



Two alumina custom components showing a threaded hexagonal body and flanged end

Alumina Custom Components

Product reference: alumina-custom-components

Material: Alumina

Product type: Custom Alumina Ceramic Component

Drawing-based alumina components with threaded bores, hexagonal profiles, shoulders and flanges for application-specific equipment interfaces.

Alumina Typical Material Properties

Property	95% Al ₂ O ₃	99% Al ₂ O ₃	99.5% Al ₂ O ₃	99.8% Al ₂ O ₃	Condition / basis
Density (g/cm ³)	3.65	3.85	3.90	3.92	-
Fracture toughness (MPa·m ^{1/2})	3-4	3-4	4	4	-
Young's modulus (GPa)	320	340	370	390	-
Flexural strength (MPa)	300	330	375	390	25°C
Compressive strength (MPa)	2200	2350	2450	2500	25°C
Thermal conductivity (W/(m·K))	18-22	27	29	32	25°C
Linear thermal expansion coefficient (10 ⁻⁶ /K)	8	8	8	8	25-1000°C
Dielectric strength (kV/mm)	16	20	22	22	-
Volume resistivity (Ω·cm)	10 ¹⁴	10 ¹⁴	10 ¹⁴	10 ¹⁴	25°C
Relative permittivity	9	9.7	9.7	9.8	1MHz, 25°C
Dielectric loss	0.0004	0.0002	0.0002	0.0001	1MHz, 25°C
Vickers hardness (HV)	>1300	1700	1750	1800	-
Material thermal-shock temperature difference, ΔT (°C)	220	180-200	180-200	180-200	-

Property	95% Al ₂ O ₃	99% Al ₂ O ₃	99.5% Al ₂ O ₃	99.8% Al ₂ O ₃	Condition / basis
Typical maximum material temperature (°C)	1500	1650	1700	1700	-

Product Geometry & Configuration

Product parameter	Configuration	Basis
Material	Alumina ceramic	Grade and purity selected for the service environment
Threaded interface	Internal thread	Designation, pitch, engagement length and acceptance method on the drawing
Outer profile	Hexagonal body, reduced neck and circular flange	Across-flats, overall length, neck diameter and flange dimensions on the drawing
Locating surfaces	Recessed bore, shoulders and flange faces	Mating fit, alignment and surface finish on the drawing
Other forms	Custom shoulders, bores and mounting interfaces	Manufacturing feasibility and drawing review